

Columbia Coatings

# Technical Data Sheet

Columbia Coatings  
1173 Industrial Park Rd  
Columbia, TN 38401  
931-388-7730  
931-388-5573 FAX



<b>Number:</b>	M36750602
<b>Name:</b>	Rose Gold Glitz II
<b>Type:</b>	Hybrid

## Powder Properties

<b>Specific Gravity</b>	1.65 g/cm <sup>3</sup>
<b>Storage Temp</b>	< 80°F (27°C) up to 1 year
<b>Theoretical Coverage</b>	117 ft <sup>2</sup> /lb. @ 2 mils
<b>Particle Distribution</b>	25 - 50 MICRONS AVERAGE

## Coating Properties

<b>Film Thickness</b>	Recommended Film Thickness: 2 mils
<b>KV Settings</b>	Recommended KV Settings: 20 – 40 KV
<b>Cure Schedule</b>	Metal Temperature: 10 minutes @ 400°F (204°C)
<b>Gloss Level</b>	20% – 30% @ 60°
<b>Pencil Hardness</b>	H – 2H
<b>Flexibility</b>	100%
<b>Adhesion</b>	4B
<b>Direct Impact</b>	160 in-lb. direct
<b>Reverse Impact</b>	160 in-lb. reverse
<b>Salt Spray</b>	1000 hrs. less than 1/16" in creepage over B-1000 treated test panels (ASTM B117)

[www.columbiacoatings.com](http://www.columbiacoatings.com)